

REEL OF YARN BOBINO FILASSE

Functionality

Superior quality combed linen yarn on the reel.

- Used in addition to jointing compounds for sealing metal threaded connections with hot or cold water.
- Improves the pressure resistance of joints (especially where there is a significant clearance).
- For chemical installations, use GEBETANCHE HYDROCARBURES (HYDROCARBONS).
- For plastic connections, use PATE D'ETANCHEITE MATERIAUX PLASTIQUES (SEALING PASTE FOR PLASTIC MATERIALS).

Technical characteristics

Characteristics	Specifications
Quality	Extra fine, Water ret
Temperature resistance	+140°C
Properties	Good water resistance Good bacterial resistance

Use

Preparation

- Degrease the connections with solvent such as acetone.

Instructions for use

- Coat the male and female joints with the jointing compound most suited to the conditions of use (type and temperature of the fluid, type of joint, condition of the threads).
- Wrap the yarn around the male fitting in the direction of the thread and smooth out.
- Apply more jointing compound to the male connector over the yarn.
- Assemble and tighten firmly.

Consumption

Depends on the condition of the thread.

Make sure the the yarn is well spread out on the thread when winding.

Safety precautions

The Material Safety Data Sheet is available on the Internet on www.quickfds.com or on www.geb.fr .

If the product is subject to detergent regulation : Component list available on request at reach@geb.fr

If the product is subject to biocide regulation or if it contains a biocide to protect it : Consult the Material Safety Data Sheet - Please use the products responsibly.

Tip

Smooth the piece of yarn between your fingers to eliminate any knots that may hinder screwing the joints together.

Storage

Store at a temperature between 0°C and +40°C.

The expiry date on packaging is for unopened product stored at 20°C in normal hygrometry conditions.

Packaging and waste sorting

Refer to the information on the product and to the applicable local regulations.

The information contained on the technical datasheet is provided in all good faith and results from measurements made in our laboratory. Given the number of materials, differences in quality and diversity of working methods, we recommend that users perform tests prior to application under actual conditions of use.

This document may be amended in keeping with product development and the state of our knowledge without prior notice and therefore it is recommended to check on <http://www.geb.fr> that you have the latest version before use.