

COLLE FIX'

Functionality

Single-component, moisture-curing MS-Polymer/STP (Silane-Terminated Polymer) adhesive that combines high performance and practicality. Solvent-free.

- Allows many substrates to be fixed without drilling, even damp substrates up to 16kg/cm².
- Practical, it's just the right amount for all your everyday collages in a handy format. No mess thanks to a 80 mL tube.
- Indoor or outdoor bonding of even heavy components (shelves, mirrors, washbasins, towel rails, mouldings, coat hooks, door knobs, panelling, wall panels, skirting boards, polystyrene components, trays, air vents, electrical boxes, acoustic insulations, etc.).

Technical characteristics

Characteristics	Specifications
Colour	White
Appearance	Thixotropic paste (does not run)
Type of mastic	Neutral MS polymer-based elastomer mastic-glue
Odour	None
Time of film formation	10 - 15 min
Cross-linking speed	3 mm the first 24 H
Application temperature	+5°C to +40°C
On cross-linked product	
Shore A hardness	34
Modulus 100%	0.9 MPa
Elongation at break	400 %
Load resistance ¹	16 kg/cm ²
Temperature resistance	-20°C to +90°C
Resistance	Very good resistance to ageing, weathering and UV rays
Adhesion	Excellent on all standard porous and non-porous surfaces, even damp (enamel, acrylic materials, stoneware, steel, stainless steel, electro-galvanised steel, raw and anodised aluminium, concrete, wood, glass, PVC, polycarbonate, painted surfaces, except bitumen, PE, PP and PTFE).
Paintability	Yes, with acrylic paint Comment: - On a seal subject to considerable movement, the paint can only crack off through lack of sufficient elasticity.

	- We recommend painting on the joint when damp or within 2 hours following application. Beyond this time, application problems can occur with some paints.
--	--

¹ maximum value observed on a bond with porous or non-porous substrates subjected to shear stress.

Comment: All of this data is given for 23°C and 55% of relative humidity. According to the cross-linking conditions, these values may therefore vary

Use

Preparation

- The surfaces must be clean and free of grease (using alcohol or acetone for example, depending on the surface).

Instructions for use

- For plastic surfaces, it is best to remove any "shine" from the surface to be glued using gentle abrasion (sandpaper 120 or fine steel wool).
- Apply the product in a spaced out straight beads, in a zigzag pattern or in dots, covering the whole surface to be glued, making sure that it is not too thick. On flat surfaces, beads of 2 mm diameter are adequate.
- Position the object to be fixed by pressing firmly.
- Maintain the bond for approximately 1 minute (example of elements: wooden peg, PVC soap dish, 120x120 mm tiling). Wait at least 12 hours before using the bonded item.
- For heavy objects, support and wait at least 24 hours (time to be adjusted according to the weight of the item being bonded).

Consumption

An 80ml tube contains approximately 4m of 5mm diameter adhesive.

Material cleaning

Excess fresh putty can be removed with white spirit or acetone.

Safety precautions

The Material Safety Data Sheet is available on the Internet on www.quickfds.com or on www.geb.fr .

If the product is subject to detergent regulation : Component list available on request at reach@geb.fr

If the product is subject to biocide regulation or if it contains a biocide to protect it : Consult the Material Safety Data Sheet - Please use the products responsibly.

Comments

For use on natural stone (marble, granite, etc.), we recommend that you carry out a test on a concealed area first.

Non-corrosive to metals

Storage

Store at a temperature between -5°C and +30°C.

The expiry date on packaging is for unopened product stored at 20°C in normal hygrometry conditions.

Packaging and waste sorting

Refer to the information on the product and to the applicable local regulations.

The information contained on the technical datasheet is provided in all good faith and results from measurements made in our laboratory. Given the number of materials, differences in quality and diversity of working methods, we recommend that users perform tests prior to application under actual conditions of use.

This document may be amended in keeping with product development and the state of our knowledge without prior notice and therefore it is recommended to check on <http://www.geb.fr> that you have the latest version before use.