

Technical Data Sheet

F-Labo-044 V11

Issued on: 26/09/2025

Version: 1

Cancels and replaces previous versions

DECAPANT PRO PISCINE

Functionality

Solvent for preparing U-PVC, C-PVC, flexible PVC and ABS pipe components.

- Improves bonding by solubilising the moulding surface.
- Suitable for use with COLLE PRO PISCINE, and all other adhesives for PVC-U and flexible PVC.
- Do not use on threaded plastic fittings, use an alcohol instead.

Technical characteristics

Characteristics	Specifications
Appearance	Clear liquid
Colour	Colourless
Odour	Ketonic
Density at 20°C	0.8

Use

Preparation

- Before use the stripper, abrade the parts to be assembled with sand paper.
- Check the presence of the bevel on the end of the male part of the pipe or fitting. If the pipe is cut on site, restore this bevel with a file or other process resulting in the same profile.

Instructions for use

- Strip the two parts to be assembled with a clean cloth soaked in DECAPANT PRO PISCINE.
- Wait for the stripper to evaporate completely, then apply COLLE PRO PISCINE.
- For all other adhesives follow instructions on the pack and/or the manufacturer's technical data sheet.

Safety precautions

The Material Safety Data Sheet is available on the Internet on www.quickfds.com or on www.qeb.fr.

If the product is subject to detergent regulation: Component list available on request at reach@geb.fr

If the product is subject to biocide regulation or if it contains a biocide to protect it: Consult the Material Safety Data Sheet - Please use the products responsiblly.

GEB SAS – CS 62062 – Tremblay en France - 95972 Roissy Charles de Gaulle Cedex – France Tél : 33 (0)1.48.17.99.99 - Fax : 33 (0)1.48.17.98.00 - www.geb.fr

Storage
Store at a temperature between -5°C and +35°C. The expiry date on packaging is for unopened product stored at 20°C in normal hygrometry conditions.
Packaging and waste sorting
Refer to the information on the product and to the applicable local regulations.
The information contained on the technical datasheet is provided in all good faith and results from measurements made in our laboratory. Given the number of materials, differences in quality and diversity of working methods, we recommend that users perform tests prior to application under actual conditions of use. This document may be amended in keeping with product development and the state of our knowledge without prior notice and therefore it is recommended to check on http://www.geb.fr that you have the latest version before use.
GEB SAS – CS 62062 – Tremblay en France - 95972 Roissy Charles de Gaulle Cedex – France Tél : 33 (0)1.48.17.99.99 - Fax : 33 (0)1.48.17.98.00 - www.geb.fr
T. CR. DECARANT DRO. DISCINE, page 2 aux 2